

Since 1927, Arrow-Magnolia cleaning and maintenance problems with the finest products available today.

## HIGHLIGHTS

- -Rust Shield With Alkaline Power
- -For Indoor & Outdoor Rust Protection of All Types of Metals
- -Fire Resistant Coating
- -Does Not Require Removal For Welding
- -Clear & Black Formulations

### TYPICAL PROPERTIES

-Vapor Pressure: 2.8

-Volatility: 75

**Insoluble** -Solubility:

-Specific Gravity: 0.8217

-Vapor Density: Heavier

than Air

-pH: 7.0

-Evaporation Rate: N/A

-Physical Description: Opaque

Brown Liquid w/ Solvent

Odor

## **SAFETY CAUTIONS**

- -Keep out of reach of children.
- -Use under normal atmospheric conditions in well ventilated
- -Keep containers closed when not in use.
- -Refer to SDS for additional safety information.



Flammability Health 1 0 Reactivity Personal Protection

## has helped people solve their AKKOW-MACTOR INTERNATIONAL, INC



**SINCE 1927** 

# **BAR RUST-**CLEAR

## LIQUID **DESCRIPTION:**

BAR-RUST CLEAR is a blend of specially designed inorganic corrosion inhibitors contained in a petroleum base carrier. The excellent rust protective properties of the product are obtained by a special "shingling" effect which occurs during the curing process of the applied film. Very small alkaline, plate shaped particles form a tightly coherent barrier wherein each particle overlaps the surrounding particles in the manner of shingles on the roof of a house. This tightly cohesive and adhesive barrier of "interlocking" corrosion resistant cells function as a continuous film which repels water (essential to rust formation), and protects the base metal beneath the film. BAR-RUST comes in both clear and black formulations.

## **DIRECTIONS:**

- -BAR-RUST CLEAR is designed to be applied as a concentrate (undiluted) for maximum protection for all types of metals indoors and outdoors.
- -For optimum protective properties, the surfaces of the metal being treated should be free of dirt or grease or any foreign matter which might interfere with the deposition of a continuous protective coating of the product. BAR-RUST CLEAR can be applied, however, directly over mill scale without the necessity of sand-blasting or similar surface preparation. BAR-RUST CLEAR can be applied by spraying, brushing or dipping procedures.
- -For indoor storage protection, a 2-3 mil coating will provide rust protection for an indefinite period of time under average conditions.
- -To provide outdoor storage protection for metal parts, a 2-3 mil coating will provide from six months to one year protection under severe conditions. A 5-6 mil coating will provide about two years protection under similar conditions.
- -In cases where coating film thicknesses are critical to assure protection, a mil thickness gauge should be used to provide an accurate measure of actual film thickness obtained.

manufactured by:

ARROW - MAGNOLIA INTERNATIONAL, Inc. 2646 Rodney Lane Dallas, Texas 75229 Toll Free: 800.527.2101 www.arrowmagnolia.com